



EDUARD MERKLE GMBH & CO. KG

KALK-, TERRAZZO- UND STEINMAHLWERKE 89143 Blaubeuren-Altental Tel. (073 44) 96 01-0 Fax (073 44) 96 01-11

ULMER WEISS 120 H**Chemical analysis of ULMER WEISS**

CaCO ₃	99,2	%
MgCO ₃	0,4	%
Fe ₂ O ₃	0,035	%
Al ₂ O ₃	0,1	%
SiO ₂ (Silicates)	0,25	%
Volatile matter (105°C)	(DIN EN ISO 787-2)	< 0,2 %

Physical data

Loose bulk density		1,4 g/cm ³
Density	(DIN EN ISO 787-10)	2,7 g/cm ³
Hardness (Mohs)		3
Refractive index		1,59

The above data are average values from numerous measurements, published without legal commitment.

Sieve analysis (DIN 53 734)

Percentage of particles finer than	1250 µm	99	%
	1000 µm	78	%
	800 µm	50	%
	500 µm	3	%

Mean particle size: 850 µm

Particle size distribution curve of ULMER WEISS 120 H

